

Rastede, Januar 2025

<u>Radiata-Pine Plywood III+/III WBP CE 2+</u> Technical Data Sheet (TDS)						
Product name:	Radiata pine plywood					
Production:	Plywood factories located in Xuzhou City, China					
Size:	2440 x 1220 mm / 2500 x 1250 mm					
Thickness:	9 mm, 12 mm, 15 mm, 18 mm, 20 mm, 24 mm, etc.					
Thickness tolerance:	+/- 1,0 mm			+/- 0.8 mm		
Veneer:	9 mm	12 mm	15 mm	18 mm	20 mm	24 mm
	7 plies	9 plies	11 plies	13 plies	15 plies	17 plies
	2 layers (face and back) in pine, interlayer veneers in poplar					
Construction:	CROSSWISE STRUCTURE veneers					
Glue:	WBP glue (exterior), CE EN314-2/class 2					
Hot press time:	3 times hot press, 1 time sanded and 1 side closed					
Moisture content:	At the time of shipment = 8 % - 12 %					
Density:	550 kg/m ³					
Surface:	Smooth/smooth					
Packing:	Plywood packing + iron steel bands + foil + printed shipping marks					